

# C95510 AMS 4880 Nickel Aluminum Bronze

## Chemical Composition

	Element						
	Cu <sup>(1)</sup>	Sn	Zn	Fe	Ni <sup>(2)</sup>	Al	Mn
(1) Cu + Sum of Named Elements 99.8% min.(2) Ni value includes Co.							
Min (%)	78.0			2.0	4.5	9.7	
Max (%)		0.20	0.30	3.5	5.5	10.9	1.5

## Applicable Specifications

Form	System	Standard	Description
As Centrifugal Cast	AMS	4880	Aluminum Bronze Castings, Centrifugal And Continuous Cast, Solution Heat Treated And Tempered
	SAE	J461	Wrought And Cast Copper Alloys
	SAE	J462	Cast Copper Alloys

